



TRICAT

Product Information Sheet

Standard (non-activated) 3A, 4A, 5A and 13X Zeolite Powders

Product Code	Cation	H ₂ O Ads. RH50%, 25C	CO ₂ Ads. 250mm, 25C	LOI wt%	Part. Size micron	Density g/ml	Notes
3A-38	K > 38%	> 25.5		< 21	3-5	> .70	Standard
3A-45	K > 45%	> 25.5		< 21	3-5	> .70	Medium K
3A-60	K > 60%	> 23.5		< 21	3-5	> .70	High K
3A-D-38	K > 38%	> 25		< 21	6-9	> .78	Hi Density
3A-D-45	K > 45%	> 25		< 21	6-9	> .78	Hi Density
4A	Na	> 27		< 21	3-5	> .70	Standard
4A-D	Na	> 26.5		< 21	6-9	> .75	Hi Density
4A-5	Na	> 27		< 21	< 3	> .65	Hi Capacity
5A-70	Ca > 70%	> 27		< 21	3-5	> .70	Standard
5A-90	Ca > 90%	> 27		< 21	3-5	> .70	Standard
5A-D-70	Ca > 70%	> 27		< 21	6-9	> .75	Hi Density
5A-D-90	Ca > 90%	> 27		< 21	6-9	> .75	Hi Density
13X	Na	> 32	> 22.5	< 23	3-5	> .60	Standard
13X-D	Na	> 32	> 22.5	< 23	6-8	> .68	Hi Density
13X-5	Na	> 32	> 22.5	< 23	< 3	> .58	Hi Capacity
13X-L	Na	> 32	> 22.5	< 23	3-5	> .60	Low Chloride
13X-B	Na	> 32	> 22.5	< 23	4-6	> .60	Benzene Grade
13X-C	Na	> 32	> 23	< 23	4-6	> .60	Hi Stability



TRICAT Zeolites, Molecular Sieves and Custom Catalysts

Tel: (410) 785-7900
Fax: (410) 785-7901

Headquarters
260 Schilling Circle
Hunt Valley, Maryland 21031

www.tricatgroup.com